

# FINESSE™ DPR FINISH

A Smooth 100%  
Acrylic-Based Dirt  
Pickup Resistance  
Finish



## PRODUCT DESCRIPTION

Finesse finish is a premixed 100% acrylic-based architectural finish which is offered in all Dryvit standard colors as well as custom colors. Finesse provides the finishing touch that adds lasting color to exterior and interior walls. Finesse includes DPR (dirt pick-up resistant) chemistry that will remain clean longer after application.

## USES

Finesse finish is designed to be applied over substrates such as Dryvit Outsulation systems' base coat, and properly prepared masonry, stucco, precast or cast-in-place concrete as well as other approved substrates. Finesse is trowel-applied by experienced plastering mechanics, and can be used for exterior as well as interior applications over properly prepared substrates.

## FEATURES & BENEFITS

FEATURE	BENEFIT
▪ 100% acrylic	▪ Greater flexibility for crack resistance
▪ DPR and PMR chemistry	▪ Resistant to dirt and the growth of mold and mildew
▪ Vapor permeable	▪ Will not trap moisture vapor
▪ Multiple deliveries	▪ Trowel Applied
▪ Cleans with water	▪ Less time and labor for clean up

## PROPERTIES

**Drying Time:** Drying of the Finesse finish is dependent on the air temperature, relative humidity and finish thickness. Under average drying conditions [70 °F (21 °C), 55% R. H.], the finish will dry in 24 hours. Lower temperature and higher humidity will require that the DPR finish be protected for longer periods. Protect work from rain during the drying period.

**Testing Information:** For individual test data on this product's properties, refer to the chart included with this document.

**Job Conditions:** Air and surface temperature for application of finishes must be between 40 °F (4 °C) and 100 °F (38 °C) and must remain so for a minimum of 24 hours.

**Temporary Protection:** Shall be provided at all times until the Finesse finish is dry, and installation of permanent flashings, sealants, etc. are completed to protect the wall from inclement weather and other sources of damage.

**Mock-Up:** Prior to application of Finesse finish on the project, a mock-up shall be prepared by the applicator and approved by the architect/owner to be used as the basis for acceptance. The mock-up shall be of sufficient size to properly demonstrate the proper application and aesthetics of the finish. Minimum 8 ft x 8 ft (2.4 m x 2.4 m) is recommended.

## DS859

### COVERAGE

Apply two coats of Finesse resulting in a total dry film thickness of 36 mils (DFT). Each pail contains 60 lbs (27.2 kg) of products; applying the product in two coats on a flat, non-absorbent substrate to 36 mils DFT will result in a coverage rate of 113 ft<sup>2</sup> (10.5 m<sup>2</sup>) per pail. Substrate smoothness and porosity may affect the actual coverage rate.

### STORAGE

Finesse finish must be stored at a minimum of 40 °F (4 °C) and a maximum of 100 °F (38 °C) in tightly sealed containers, protected from weather and out of direct sunlight.

The shelf life is 2 years from date of manufacture when properly stored in unopened pails.

### TEXTURE

Finesse is designed to provide a smooth finish when applied over a properly prepared surface. Final appearance will vary depending on the substrate condition, technique and skill of the installer.

### MAINTENANCE

All Dryvit products are designed to require minimal maintenance. However, as with all building products, depending on location, some cleaning may be required. See Dryvit publication DS152 on cleaning and recoating.

### CLEAN UP

Clean tools with water while the finish is still wet.



# FINESSE™ DPR FINISH

A Smooth 100%  
Acrylic-Based Dirt  
Pickup Resistance  
Finish



## SURFACE PREPARATION

- Surfaces must be smooth, planar and free of imperfections to ensure satisfactory appearance.
- Surfaces must be clean, dry, structurally sound and free of efflorescence, grease, oil, form release agents and curing compounds.
- To minimize visible trowel marks, it is recommended that areas coated with Finesse finish be separated with joints not exceeding 5 ft (1.5 m).
- **Dryvit Reinforced Base Coat:** The base coat must be dry and cured for a minimum of 24 hours before application of the finish. The double pass application method is required to minimize imperfections. The reinforcing mesh shall be completely embedded in base coat with no mesh pattern visible.
- **Concrete:** Shall have cured a minimum of 28 days prior to application of Finesse finish. All projections shall be removed and small voids filled with Dryvit Primus®, Primus® DM, Genesis® or Genesis® DM mixture (see product data sheets for mixing and application). If efflorescence, form release agents or curing compounds are present on the concrete surface, the surface shall be thoroughly washed with muriatic acid and flushed to remove residual acid.
- **Masonry:** The masonry surface, with joints struck flush, shall be skim coated with Primus, Primus DM, Genesis or Genesis DM mixture (see product data sheets for mixing and application) to produce a smooth, level surface, free of imperfections.
- **Stucco:** Shall be floated to a smooth fine sand finish. If additives are present in the stucco, a test patch shall be made and bond strength checked prior to primer application. For best results, a skim coat of Dryvit Primus, Primus DM, Genesis or Genesis DM mixture is recommended to achieve as smooth and flat a surface as possible.
- **Interior Wallboard:** Interior wallboard surfaces shall be finished to a Level 4 finish in accordance with ASTM C840.

## MIXING

Some settling of the finish may occur during shipping. Thoroughly mix the finish with a “Twister” paddle or equivalent mixing blade powered by a 1/2 in (12.7 mm) drill, 450-500 rpm, until a uniform workable consistency is attained.

## APPLICATION

Ensure that the surface is smooth, planar and free of any imperfections that would interfere with a smooth finish application. Correct any suspect areas prior to application of primer and Finesse finish.

- Apply a coat of color coordinated Color Prime™ or Primer with Sand™ and allow to dry.
- Apply the first coat of Finesse finish with a stainless steel trowel, pulling it tight to the primed surface. Apply a uniform coat sufficient to completely cover the primer, forming an opaque finish on the wall. Allow to dry a minimum of 4 hours before proceeding.
- Apply a second coat of Finesse finish in short, random strokes for complete uniform coverage of the first coat to match the approved sample.
- Allow the finish to dry for 10-20 minutes (depending on weather), then smooth it using a stainless steel trowel to densify the surface and remove loose material and blade marks.
- Protect the finish until dry.

## DS859

### CAUTIONS & LIMITATIONS

- Avoid applying finish in direct sunlight. Always work on the shady side of the wall or protect the area with appropriate shading material.
- Finesse finish must not be used on exposed exterior horizontal surfaces. Minimum slope is 1:2 (27°). Maximum length of slope shall not exceed 12 in (305 mm).
- Finesse finish shall not be used below grade when applied as the finish for an EIF System.
- Finesse finish is not designed for direct application over vertical exterior gypsum based sheathing or insulation boards.
- Finesse shall not be returned into sealant joints or other areas that will be in direct contact with sealant. Instead, a coat of Color Prime or Demandit® Smooth shall be applied over the base coat that will be in contact with the sealant.
- Smooth finishes will accentuate any imperfections of the underlying surface. Therefore, it is important that the underlying surface be prepared in a manner that will minimize textural imperfections that may result in undesirable aesthetic results. For applications over Dryvit EIFS, the base coat shall be applied using the two pass method as described in Dryvit System Application Instructions.

### TECHNICAL AND FIELD SERVICES

Available on request.



# FINESSE™ DPR FINISH

A Smooth 100%  
Acrylic-Based Dirt  
Pickup Resistance  
Finish



## FINESSE DPR FINISH TESTING

Test	Test Method	Criteria	Results <sup>1</sup>
Surface Burning Characteristics	ASTM E 84	ICC and ANSI/EIMA 99-A-2001 Flame Spread <25 Smoke Developed <450	Passed
Flexibility <sup>2</sup>	ASTM D 522 Method B	No ICC or ANSI/EIMA Criteria	Passed: 1.5" diameter @ 73 °F
Water Vapor Transmission	ASTM E 96 Procedure B	ICC: Vapor Permeable No ANSI/EIMA Criteria	40 Perms
Accelerated Weathering	ASTM G 154 Cycle 1 (QUV)	ANSI/EIMA 99-A-2001 2000 hours: No deleterious effects <sup>3</sup>	5000 hours: No deleterious effects <sup>3</sup>
	ASTM G 155 Cycle 1 (Xenon Arc)	ICC: 2000 hours: No deleterious effects <sup>3</sup>	2000 hours: No deleterious effects <sup>3</sup>
Chalk Rating	ASTM D 4214 after ASTM G 154 Cycle 1	No ICC or ANSI/EIMA Criteria	Chalk rating: 9+ after 5000 hours QUV
Instrumentally Measured Color Difference <sup>4</sup> (includes yellowing)	ASTM D 2244 CIELAB, 10° Observer after ASTM G 154 Cycle 1	No ICC or ANSI/EIMA Criteria	Color change: 0.51 Delta E after 5000 hours QUV
Freeze-Thaw Resistance	ASTM E 2485 (formerly EIMA 101.01)	ANSI/EIMA 99-A-2001 60 cycles: No deleterious effects <sup>3</sup>	90 cycles: No deleterious effects <sup>3</sup>
	ASTM E 2485 ICC - ES Proc. (AC212)	ICC: 10 cycles No deleterious effect <sup>3</sup>	10 cycles: No deleterious effects <sup>3</sup>
Mildew Resistance	ASTM D 3273	ANSI/EIMA 99-A-2001 28 days: No growth	60 days: No growth
Salt Spray Resistance	ASTM B 117	ICC and ANSI/EIMA 99-A-2001 300 hours: No deleterious effects <sup>3</sup>	1000 hours: No deleterious effects <sup>3</sup>
Water Resistance	ASTM D 2247	ICC and ANSI/EIMA 99-A-2001 14 days: No deleterious effects <sup>3</sup>	42 days: No deleterious effects <sup>3</sup>
Abrasion Resistance	ASTM D 968 Method A Falling Sand	ANSI/EIMA 99-A-2001 528 quarts (500 liters): No deleterious effects <sup>3</sup>	1057 quarts (1000 liters): No deleterious effects <sup>3</sup>
	ASTM D 4060 Taber Abrasion (1 kg load)	No ICC or ANSI/EIMA Criteria	1000 cycles: .83 mg mass loss
Adhesion to Concrete	ASTM D 4541	ICC and ANSI/EIMA 99-A-2001: 15 psi minimum	>200 psi
Tensile Bond	ASTM C 297/E 2134 (formerly EIMA 101.03)	ICC and ANSI/EIMA 99-A-2001: 15 psi minimum	>25 psi

1. Testing referenced is based on standard Dryvit finishes.

2. Finish applied over aluminum panels, bent on cylindrical mandrels as described in ASTM D 522 Method B. Lower diameter indicates higher flexibility.

3. No cracking, checking, rusting, crazing, erosion, blistering, peeling, or delamination when viewed under 5x magnification.

4. Delta E is total color difference, including yellowing, lightening, darkening, changes in red, blue, and green color values. Finish exposed to 5,000 hours of QUV prior to evaluating Delta E.

Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of Dryvit Systems, Inc. products as of the date of publication of this document and is presented in good faith. Dryvit Systems, Inc. assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Dryvit Systems, Inc.

For more information on [Dryvit Systems](#) or [Continuous Insulation](#), visit these links.

Printed in USA. Issued 05-01-17  
©Dryvit Systems, Inc. 2014



Dryvit Systems, Inc.  
One Energy Way | West Warwick, RI 02893  
(800) 556-7752 | [www.dryvit.com](http://www.dryvit.com)